

H660I Reflective Tape Data Sheet

	Reflective Tape (Commercial Grade)	Testing Method
Material Thickness (mm)	0.128 PET	--
Total Applied Thickness	0.24 mm	Caliper Method
Adhesive Thickness (mm)	0.02 mm Water Acrylic	--
Overall Thickness (mm)	0.148 mm	--
Initial Tack (no.)	24	J.Dow Method
Peeling Strength (kg/inch)	1.0	PSTC-1
Holding Power (HR)	72	PSTC-7

Temperature: 25°C

Humidity: 60-70%

Testing Report and Commercial Grade

Observation Angle	Entrance Angle	Measured Value			Standard Value
		Y4	Y5	Y6	White Colour
12°	5°	43	40	39	35
	30°	23	26	26	18
	40°	12	16	15	7.0
20°	5°	33	31	29	25
	30°	19	20	18	12
	40°	11	11	13	6.0
2°	5°	9	10	7	4.0
	30°	6	7	9	1.8
	40°	5	6	5	1.0

LRV Test Results

Material/Colour	Av. LRV	Range
H660IB	7	2
H660IV	41	4
H660IO	28	3
H660IR	14	2
H660IW	85	0
H660IY	65.25	2